



G48® Data Sheet

D/EVO 017 e February 2017
Supersedes edition of July 2016

Page 1 of 5

Glysantin® G48® is an engine coolant concentrate based on ethylene glycol that needs to be diluted with water before use.

Glysantin® G48® contains a corrosion inhibitor package based on salts of organic acids and silicates (Hybrid Coolant).

Glysantin® G48® is free of nitrites, amines and phosphates.

Properties

Glysantin® G48® was developed to protect engines against corrosion, overheating and frost damage. It gives a high degree of corrosion protection to engine components such as radiators, cylinder blocks/heads, water pumps and heat exchangers, and avoids deposits.

Glysantin® G48® fulfills the requirements of the following coolant standards:

AS 2108-2004, ASTM D3306, ASTM D4985, SAE J1034, AFNOR NF R 15-601, ÖNORM V 5123, CUNA NC 956-16, JIS K 2234:2006, SANS 1251:2005, PN-C-40007, China GB 29743-2013 and BS 6580:2010.

Furthermore Glysantin® G48® is officially approved by:

- BMW BMW GS 94000
- Bez. Reg. Arnsberg, 84.12.22.63-2001-2
Dept. of Mining and Energy
- German Army TL 6850-0038/1
- Daimler / Mercedes-Benz MB-Approval 325.0
- Deutz DQC CA-14
- Jenbacher TA-Nr. 1000-0201
- Liebherr Minimum LH-00-COL3A
- MAN MAN 324-NF
- MTU MTL 5048
- Opel / General Motors B 040 0240
- Porsche for 924, 928, 944, 968
- Saab 6901599
- VW / Audi / Seat / Skoda TL 774-C



G48® Data Sheet

D/EVO 017 e February 2017
Supersedes edition of July 2016

Page 2 of 5

Miscibility

Since the special advantages of Glysantin® G48® will only be achieved when Glysantin® G48® is used exclusively, mixing Glysantin® G48® with other Glysantin coolants or products from other producers is not recommended.

Glysantin® G48® should be blended with water in a concentration amongst 33 to 60% by volume prior to infilling. The usage of a 50/50 ratio for the mixture of water and Glysantin is generally advisable.

For preparation of the coolant it is recommended to use distilled or deionized water. In most cases tap water is also appropriate.

Analysis values of the water may not exceed the following threshold values:

Water hardness:	0 – 2.7 mmol/l
Chloride content:	max. 100 ppm
Sulphate content:	max. 100 ppm

Chemical nature

Ethylene glycol with corrosion inhibitors

Appearance

Clear liquid

Physical data

Density, 20 °C	1.121 – 1.123 g/cm ³	DIN 51 757-3
Viscosity, 20 °C	24 – 28 mm ² /s	DIN 51 562
Refractive index, 20 °C	1.432 – 1.434	DIN 51 423-2
Boiling point	> 165 °C	ASTM D1120
Flash point	> 120 °C	DIN EN ISO 2592
pH value	7.1 – 7.3	ASTM D1287
Reserve alkalinity	13 – 15 ml	ASTM D1121
Ash content	max. 1.5 %	ASTM D1119
Water content	max. 3.5 %	DIN 51 777-1



G48[®] Data Sheet

D/EVO 017 e February 2017
Supersedes edition of July 2016

Page 3 of 5

Frost protection


Freezing point

ASTM D1177

50 vol % solution below -38 °C

33 vol % solution below -18 °C

Frost Protection of Glysantin[®] G48[®]



Foaming characteristics

33 vol % solution

max. 50 ml / 3 s

ASTM D1881

Electrical conductivity

30-50 vol % solution

approx. 4 mS/cm, at 25 °C

ASTM D1125

Glassware Corrosion Test

ASTM D1384

Metal coupons	typical weight loss mg/coupon	ASTM D3306 limit mg/coupon
Copper	0.1	10 max
Solder	0.3	30 max
Brass	0.2	10 max
Steel	-0.2 *)	10 max
Cast iron	-1.0 *)	10 max
Cast aluminum	-1.1 *)	30 max

*) remark: negative values mean a weight gain



G48® Data Sheet

D/EVO 017 e February 2017
Supersedes edition of July 2016

Page 4 of 5

Heat Transfer Corrosion Test	ASTM D4340	typical corrosion rate	ASTM D3306 limit
		mg/cm ² /week	mg/cm ² /week
	Cast aluminum	-0.07 *)	1.0 max

Simulated Service Corrosion Test	ASTM D2570	Metal coupons	typical weight loss	ASTM D3306 limit
			mg/coupon	mg/coupon
		Copper	8.8	20 max
		Solder	0.0	60 max
		Brass	10.7	20 max
		Steel	0.1	20 max
		Cast iron	-1.1 *)	20 max
		Cast aluminum	-1.2 *)	60 max

*) remark: negative values mean a weight gain

Cavitation Erosion Corrosion Test	ASTM D2809	Rating	ASTM D3306 limit
			Rating
	Aluminum water pump	9	8 min

Quality Control
The above-listed data represent average values at the time of going to press of this Data Sheet. They are intended as a guide to facilitate handling and cannot be regarded as specified data. Specified product data are issued as a separate product specification.

Storage Stability
Glysantin G 48 has a shelf life of at least three years when stored in originally closed, air-tight containers at temperatures of maximum 30 °C. Do not use galvanized containers for storage.



G48[®] Data Sheet

D/EVO 017 e February 2017
Supersedes edition of July 2016

Page 5 of 5

Color

Glysantin[®] G48[®] is usually available in blue-green. Different colors may be seen in special cases.

Safety

When using this product, the information and advice given in our Safety Data Sheet should be observed. Due attention should also be given to the precautions necessary for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

February 2017

www.glysantin.de

BASF SE
Fuel and Lubricant Solutions
67056 Ludwigshafen, Deutschland

®=registered trademark of BASF SE